(19) World Intellectual Property Organization International Bureau





(43) International Publication Date 10 April 2003 (10.04.2003)

PCT

(10) International Publication Number WO 03/029163 A2

(51) International Patent Classification⁷: C04B 28/00

(21) International Application Number: PCT/EP02/09528

(22) International Filing Date: 26 August 2002 (26.08.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data: 0123364.2 28 September 2001 (28.09.2001) GB

(71) Applicant (for all designated States except US): MBT HOLDING AG [CH/CH]; Vulkanstrasse 110, CH-8048 Zürich (CH).

(72) Inventor; and

(75) Inventor/Applicant (for US only): ANGELSKAAR, Terje [NO/CH]; Honeretshof 6, Berg Dietikon, CH-8962 Zürich (CH).

(74) Agent: MCSTEA, John, Anthony; Vulkanstrasse 110, CH-8048 Zürich (CH).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

 without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

3/029163 A

(54) Title: ACCELERATOR COMPOSITION

WO 03/029163 PCT/EP02/09528

ACCELERATOR COMPOSITION

This invention relates to cementitious compositions and to accelerating admixtures for use therein, especially as accelerators for sprayed concrete.

Sprayed concrete or "shotcrete", which is applied to substrates such as rock faces and tunnels by spraying, must set very rapidly. In such a use, the traditional concrete accelerators such as calcium chloride are not effective, and there must be used more powerful accelerators, such as sodium aluminate and alkali metal hydroxides. These are highly alkaline, which gives rise both to handling difficulties and unpleasant conditions when spraying in confined spaces such as tunnels.

As a result, a new generation of alkali-free accelerators has been developed. These are based on aluminium compounds, usually the hydroxide, sulphate or basic sulphate. To these essential components have been added other components, such as alkanolamines and alkanolamine sulphates.

These aluminium-based accelerators have been very successful. However, most of them suffer from the major drawback of inadequate stability. Many such accelerators are aqueous solutions or dispersions with high solids contents (in the case of solutions, close to saturation), and if kept stored for a prolonged period, especially in high ambient temperatures, dissolved material may come out of the solution, or dispersed material may settle, or the aqueous accelerator may gel. All these things can reduce the effectiveness of the accelerator considerably or even completely.

One of the ways in which it has been sought to overcome this stability problem is to add a stabilising material. For example, in PCT published application WO 01/42165, there is disclosed the use of stabilising materials selected from hydroxycarboxylic acids, phosphoric acids and non-alkaline salts of phosphoric acids, added at the rate of up to 0.06 mol/kg. of final product at the end of the manufacturing process.

It has now been found that the reaction of aluminium compounds with a plurality of acids can give an accelerator of excellent performance and stability. The invention therefore provides an

accelerator for sprayed cementitious compositions, which is the reaction product in aqueous medium of amorphous aluminium hydroxide, aluminium sulphate, formic acid and phosphoric acid.

5 The invention additionally provides a method of preparation of an accelerator for sprayed cementitious compositions by the reaction of amorphous aluminium hydroxide, aluminium sulphate, formic acid and phosphoric acid in an aqueous medium.

The aluminium sulphate used may be any such commercially-available material. Aluminium sulphates differ in their purity and constitution, the most common being so-called "17 %" because it contains 17% of Al₂O₃. In practical terms, the weight percentage of 17 % aluminium sulphate, Al₂(SO₄)₃. 14.3 H₂ O that should be used in the process according to the invention lies in the range of from 30 % to 60 %, preferably from 40 %-48 %.

15 The aluminium hydroxide may be any commercially-available amorphous aluminium hydroxide. Although all such aluminium hydroxides will give satisfactory results, it is generally true that the more recent the date of manufacture, the better the result. In addition, aluminium hydroxides which, as a result of their particular manner of manufacture, contain a small proportion of aluminium carbonate (up to 5 %) are easier to dissolve and are preferred materials. This behaviour is not obtained by simply adding aluminium carbonate to pure aluminium hydroxide.

Formic acid and phosphoric acid (H₃ PO₄) are readily-available commercial materials.

25 The proportions of the essential ingredients, as percentages by weight of the total accelerator (excluding water) are as follows:

| | · | <u>limits</u> | preferred |
|----|---|---------------|---------------|
| | aluminium hydroxide | 10-25 | 16-20 |
| | aluminium sulphate (as Al ₂ O ₃) | 30-60 | 40-50 |
| 30 | formic acid | 0.5-15 | 6-10 combined |
| | phosphoric acid | 0.45-15 | acids |

In addition to these essential ingredients, there may additionally be present a number of other components, whose presence improves performance and which presence is therefore preferred.

- 5 The first of these is amine. This must be water-soluble, otherwise there is no restriction on the choice of amine. Preferred amines are alkanolamines, such as diglycolamine, diethanolamine and triethanolamine, diethanolamine being particularly preferred. Up to 5% by weight amine may be used, preferably from 0.5-1.5 %.
- 10 The second preferred additional component, defoaming agent, may be any such material known to the art. Most of these are proprietary commercial materials whose precise composition is never revealed, but any such material known to the art is suitable. Typical examples include silicone types such as AGITAN (trade mark) and fatty acid polyether types such as LUMITEN (trade mark) EL.

15

The defoaming agent may be used at a rate out up to 5% (solids by weight of the whole composition), preferably from 0.5%-1%. The use of defoaming agent makes the use of less fresh aluminium hydroxides easier. Surprisingly, provided that the defoamer contains no silicone and that it is not present to the extent of more than 1%, it gives an appreciable improvement in setting time over that of an identical composition without defoaming agent or with silicone types.

The invention additionally provides a method of preparing an accelerator for cementitious compositions, comprising the reaction in aqueous medium of amorphous aluminium by hydroxide, aluminium sulphate, formic acid and phosphoric acid.

The accelerator according to this invention may be manufactured using standard equipment and methods well known to those of ordinary skill in the art.

30 There are several different possible orders of addition of the components in the manufacture of the accelerator of the invention. In one method, the order of addition of the components to water is: aluminium sulphate, formic acid, phosphoric acid, aluminium hydroxide, amine

and/or defoaming agent (if desired). An alternative is: aluminium sulphate, amine, formic acid, phosphoric acid, aluminium hydroxide, amine and/or defoaming agent (if desired).

The accelerators of this invention are very stable, with shelf lives of several months at normal temperatures and of several weeks in the warm conditions sometimes encountered in storage areas on site. In addition, they perform as accelerators as well as, or better than commercially-available alkali-free accelerators.

The invention therefore also provides a method of accelerating the set of a cementitious composition applied by spraying through a nozzle, comprising the addition at the nozzle of an accelerating quantity of an accelerator as hereinabove described.

A typical dosage of accelerator added at the nozzle is from 5% - 7% by weight of the accelerator by weight of cement.

15

The invention is further described with reference to the following non-limiting examples.

(a) <u>Preparation of accelerator</u>

The following materials are used:

20

25

aluminium sulphate (17 %) (AS)
amorphous aluminium hydroxide (AH)
formic acid (FA)
phosphoric acid (PA)
diethanolamine (DEA)

The process used in this example is as follows:

Water is heated to 45 °C and gently stirred. The aluminium sulphate is added to this water.

The temperature is gradually raised to 58°C, and stirring is continued until the aluminium sulphate is completely dissolved. To this stirred solution, formic acid is slowly added, followed by phosphoric acid. The rate of stirring is then increased and aluminium hydroxide is gradually added. This is followed by the addition of diethanolamine, and stirring at the

WO 03/029163 PCT/EP02/09528

5

increased rate is continued for one hour. Stirring is then stopped and the composition allowed to cool.

Using this process a number of accelerators are prepared, and their details are shown in 5 Table 1. The figures are percentages by weight of the total accelerator (including water).

(b) Stability testing

The stability of the accelerators of Examples 1-9 is assessed at various temperatures - the higher the temperature the less likely is an accelerator to remain stable.

10

The results are shown in Table 2. A blank in the table means that the particular phenomenon (gelling, crystallisation, etc.) did not occur.

Table 1

| 10 | 42 | 18 | 0.68 | 6.12 | 1 | 30.90 | clear | 10:90 |
|-------------|----|------|------|------|-----|-------|------------|----------|
| 6 | 42 | 18 | 6.12 | 0.68 | 1 | 30.89 | clear | 90:10 |
| ∞ | 42 | 18 | 5.1 | 1.7 | | 30.73 | clear | 75:25 |
| 7 | 42 | 18 | 3.4 | 3.4 | 1 | 30.5 | clear | 50:50 |
| 9 . | 42 | .18 | 1.7 | 5.1 | 1 | 30.2 | clear | 25:75 |
| 5 | 42 | . 18 | • | 8.9 | . 1 | 29.95 | clear | 0:100 |
| 4 | 42 | 18 | 6.8 | | 1 | 31.0 | clear | 100:0 |
| 3 | 42 | 18 | 6.3 | 0.3 | 1 | 30.92 | opaque | 92.5:7.5 |
| 2 | 42 | 18 | 6.38 | 0.42 | 1 | 30.93 | opaque | 94:4 |
| 1 | 42 | .18 | 6.5 | 0.3 | - | 30.95 | opaque | 96:4 |
| Example Nr. | AS | AH | FA | . PA | DEA | Water | appearance | FA:PA |

Table 2

| | - | | | | -,- | | 1 | | | ····· | |
|---------------------|----------------|----------------|-----|------|----------------|----|---------------|-------------|---|-------|-----|
| ion | ys | 40°C | | | | | | | | | • |
| Crystallisation | Afterdays | 35°C | | • | | | • | | | | |
| P. | A | 30°C 35°C 40°C | | | | | | ٠ | | | |
| 15 H | | 40°C | | | | | | | | | |
| Gelling after | days | 35°C | | · | • | | | | | | |
| Ď | F | 30°C 35°C 40°C | | | | , | | • | | | |
| tion | ys | 40°C | 16 | 16 | 16 | 12 | | | • | | |
| Layer separation | after days | 30°C 35°C 40°C | 27 | 27 | 27 | | | | | | |
| Lay | af | 30°C | | | | | • | ÷ | | | |
| ayer | .days | 40°C | 16 | 16 | 16 | 12 | | | | 18 | 1,4 |
| Precipitated layer | >1mm afterdays | 35°C | 30 | 30 | 30 | 22 | | | | | , |
| Prec | >1mr | 30°C | | | | | | · | | | |
| idity | | 40°C | 9 | 9 . | 9 | 5 | | | | 7 . | 7 |
| Change in turbidity | after days | 35°C | 14 | . 14 | 14 | 7 | | | | 12 | 12 |
| Chan | afi | 30°C | 21 | 21 | 21 | 13 | | | | | 70 |
| Example | No. | | . 1 | 2 | 3 | 4 | . 5 | 9 | 7 | 8 | 6 |

3. Paste testing

5

A cement paste composition is made by adding 300 grams of Portland cement (CEM I 42.5) to water, to give a paste with a water/cement ratio of 0.3. There is additionally added 1 gram of a superplasticiser (GLENIUM[®] 51, a polycarboxylate superplasticiser is used).

Samples of this paste are dosed with the accelerators of Examples 4-10 at 6% by weight accelerator by weight of cement, and they are tested using Vicat needles for initial and final set. The results are as follows:

| 10 | Example No. | Initial set | Final set |
|------|-------------|-------------|-----------|
| | | (m.s.) | (m.s.) |
| | 4 · | 7.00 | 22.00 |
| • | 5 | 9.00 | 29.00 |
| | 6 | 7.00 | 23.00 |
| 15 · | 7 | 8.00 | 24.00 |
| • | 8 | 7.00 | 19.00 |
| | 9 . | 8.00 | 22.00 |
| | 10 | 6.50 | 22.00 |

Claims:

- 1. An accelerator for sprayed cementitious compositions, which is the reaction product in aqueous medium of amorphous aluminium hydroxide, aluminium sulphate, formic acid and phosphoric acid.
- 2. An accelerator according to claim 1, in which the amorphous aluminium hydroxide contains a proportion of aluminium carbonate, produced during the manufacture of the aluminium hydroxide.

10

5

3. An accelerator according to claim 1 or claim 2, in which the proportions of the components of the accelerator are present as follows:

| | | <u>limits</u> | preferred |
|----|---|---------------|---------------|
| 15 | aluminium hydroxide | 10-25 | 16-20 |
| | aluminium sulphate (as Al ₂ O ₃) | 30-60 | 40-50 |
| | formic acid | 0.5-15 | 6-10 combined |
| | phosphoric acid | 0.45-15 | ∫acids |

- An accelerator according to any one of claims 1-3, in which the accelerator additionally contains at least one of an amine and a defoamer.
 - 5. An accelerator according to claim 4, in which the amine is an alkanolamine, preferably diethanolamine.

25

- 6. A method of preparing an accelerator for cementitious compositions, comprising the reaction in aqueous medium of amorphous aluminium hydroxide, aluminium sulphate, formic acid and phosphoric acid.
- A method according to claim 6; in which the reaction is carried out by adding to water the components in an order selected from one of the following:

WO 03/029163 PCT/EP02/09528

10

- (i) aluminium sulphate, formic acid, phosphoric acid, aluminium hydroxide, amine and/or defoaming agent (if desired); and
- (ii) aluminium sulphate, amine, formic acid, phosphoric acid, aluminium hydroxide, amine and/or defoaming agent (if desired).

8. A method of accelerating the set of a cementitious composition applied by spraying through a nozzle, comprising the addition at the nozzle of an accelerating quantity of an accelerator that is the reaction product in aqueous medium of amorphous aluminium hydroxide, aluminium sulphate, formic acid and phosphoric acid.

10

(19) World Intellectual Property Organization International Bureau





(43) International Publication Date 10 April 2003 (10.04.2003)

PCT

(10) International Publication Number WO 03/029163 A3

- (51) International Patent Classification⁷: C04B 40/00, 28/02 // (C04B 28/02, 22:06, 22:14, 22:16, 24:04), 103/10
- (21) International Application Number: PCT/EP02/09528
- (22) International Filing Date: 26 August 2002 (26.08.2002)
- (25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

0123364.2 28 Septem

28 September 2001 (28.09.2001) GB

- (71) Applicant (for all designated States except US): MBT HOLDING AG [CH/CH]; Vulkanstrasse 110, CH-8048 Zürich (CH).
- (72) Inventor; and
- (75) Inventor/Applicant (for US only): ANGELSKAAR, Terje [NO/CH]; Honeretshof 6, Berg Dietikon, CH-8962 Zürich (CH).
- (74) Agent: MCSTEA, John, Anthony; Vulkanstrasse 110, CH-8048 Zürich (CH).

- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- (88) Date of publication of the international search report: 4 September 2003

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



/029163

(54) Title: ACCELERATOR COMPOSITION

INTERNATIONAL SEARCH REPORT

Internation No PCT/EP 02/09528

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 C04B40/00 C04B28/02 C04B103:10

//(C04B28/02,22:06,22:14,22:16,24:04),

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 CO4B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

| C. DOCOI | MENIO CONSI | DEVED IO | DC WETE | LVANI |
|----------|-------------|----------|---------|-------|
| | | | | |
| | | | | |

| Category ° | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
|------------|--|-----------------------|
| Y | WO 01 42165 A (HOFMANN THOMAS ;MBT HOLDING AG (CH)) 14 June 2001 (2001-06-14) cited in the application the whole document | 1-7,9 |
| Ϋ́ | WO 00 78688 A (HOFMANN THOMAS ;MBT HOLDING AG (CH)) 28 December 2000 (2000-12-28) page 2, line 1 -page 3, line 25 | 1-7,9 |
| Α | WO 98 18740 A (LUNKENHEIMER RUDOLF; SEDELIES REINHOLD (DE); ALTMANN HORST (DE); B) 7 May 1998 (1998-05-07) page 3, line 1-29 | |
| | | |

| Further documents are listed in the continuation of box C. | χ Patent family members are listed in annex. |
|---|---|
| Special categories of cited documents: 'A' document defining the general state of the art which is not considered to be of particular relevance 'E' earlier document but published on or after the international filing date 'L' document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) 'O' document referring to an oral disclosure, use, exhibition or other means 'P' document published prior to the international filing date but later than the priority date claimed | 'T' later document published after the international filing date or priorily date and not in conflict with the application but cited to understand the principle or theory underlying the invention 'X' document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone 'Y' document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. '&' document member of the same patent family |
| Date of the actual completion of the international search 23 April 2003 | Date of mailing of the International search report $08/05/2003$ |
| Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016 | Authorized officer Gattinger, I |

INTERNATIONAL SEARCH REPORT

Information on patent family members

Internation No
PCT/EP 02/09528

| Patent document cited in search report | | Publication date | | Patent family member(s) | Publication date |
|--|---|---------------------|--|---|--|
| WO 0142165 | А | 14-06-2001 | AU BR CN WO EP | 2671901 A 0016261 A 1407954 T 0142165 A2 1237827 A2 | 18-06-2001 20-08-2002 02-04-2003 14-06-2001 11-09-2002 |
| | | | NO US | 20022662 A 2002195026 A1 | 08-08-2002 26-12-2002 |
| WO 0078688 | A | 28-12-2000 | WO EP JP NO | 0078688 A1 1114004 A1 2003502269 T 20010774 A | 28-12-2000 11-07-2001 21-01-2003 15-02-2001 |
| WO 9818740 | A | 07-05-1998 | WO AT CZ DE DK EP FI GR NO PL SK US | 9818740 A1 196453 T 9901399 A3 59605932 D1 946451 T3 0946451 A1 990920 A 3035038 T3 2001509124 T 2000052720 A 991769 A 332831 A1 51599 A3 6302954 B1 | 07-05-1998 15-10-2000 17-11-1999 26-10-2000 13-11-2000 06-10-1999 23-04-1999 30-03-2001 10-07-2001 25-08-2000 14-04-1999 11-10-1999 10-12-1999 16-10-2001 |